TARDEC



Technical Report

No. 13619

Recycling MIL-H-46170 Hydraulic Fluid to Extend Fluid Service Life

March 1995

By Ellen M. Purdy
Donna M. Rutkowski
Franklyn D. Sterling

U.S. Army Tank-Automotive Command
Research, Development and Engineering Center
Warren, Michigan 48397-5000

The findings in this report are not to be construed as an official Department of the Army position unless so designated by other authorized documents.

Citation of manufacturer's or trade names does not constitute an official endorsement or approval of the use thereof.

Destroy this report when it is no longer needed. Do not return it to the originator.

REPORT DOCUMENTATION PAGE

Form Approved
OMB No. 0704-0188

1. AGENCY USE ONLY *(Leave blank)*	2. REPORT DATE	3. REPORT TYPE AND DATES COVERED
	March 1995	Final 1 Oct 93 - 31 Aug 94

4. TITLE AND SUBTITLE
Recycling MIL-H-46170 Hydraulic Fluid to Extend Fluid Service Life

5. FUNDING NUMBERS

6. AUTHOR(S)
Ellen M. Purdy
Sgt. Donna M. Rutkowski
Franklyn D. Sterling

7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES)
US Army Tank Automotive Command
Mobility Technology Center - Belvoir
ATTN AMSTA-RBF
10115 Gridley Rd, STE 128
Ft. Belvoir, VA 22060-5843

8. PERFORMING ORGANIZATION REPORT NUMBER
TARDEC-TR-13619

9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES)
Defense General Supply Center
Hazardous Materials Minimization Office
ATTN DGSC
Richmond, VA

10. SPONSORING/MONITORING AGENCY REPORT NUMBER

11. SUPPLEMENTARY NOTES

12a. DISTRIBUTION/AVAILABILITY STATEMENT
Distribution unlimited; approved for public release.

12b. DISTRIBUTION CODE

13. ABSTRACT *(Maximum 200 words)*

This report documents the laboratory efforts in proving that used hydraulic fluid could be recycled by removing contaminants and mixing with new fluid. Once the used fluid has been filtered to remove solid particulate contamination and de-humidified to bring the moisture content below 500 ppm water, it can be mixed with new fluid in a 75:25 ratio to bring the fluid mixture up to specification performance. The recycled used fluid by itself could not pass the foaming characteristic requirement thus requiring re-inhibition. Instead of adding more anti-foaming agent to the fluid, the decision was made to mix recycled fluid with new fluid to provide the re-inhibition effect. Mixing in new fluid results in an enhancement of all additive performance and eliminated any possible problems with adding too much or too little anti-foaming agent. These efforts set the standards for evaluating commercial recycling units that can recycle hydraulic fluid on a large scale and also establish doctrine for successfully extending the service life of used hydraulic fluid.

14. SUBJECT TERMS	15. NUMBER OF PAGES
Hydraulic Fluid Recycling Extended Service Life Contamination Removal Waste Minimization	22
	16. PRICE CODE

17. SECURITY CLASSIFICATION OF REPORT	18. SECURITY CLASSIFICATION OF THIS PAGE	19. SECURITY CLASSIFICATION OF ABSTRACT	20. LIMITATION OF ABSTRACT
Unclassified	Unclassified	Unclassified	UL

NSN 7540-01-280-5500

Standard Form 298 (Rev. 2-89)
Prescribed by ANSI Std. Z39-18
298-102

No. 13619

Recycling MIL-H-46170 Hydraulic Fluid to Extend Fluid Service Life

March 1995

By Ellen M. Purdy
Donna M. Rutkowski
Franklyn D. Sterling
USA Tank Automotive Command
Mobility Technology Center Belvoir
Fuels and Lubricants Division

Contents

Tables

Section 1 Introduction and Background

At the request of the Defense General Supply Center (DGSC), the Fuels and Lubricants Division of the Mobility Technology Center - Belvoir has investigated the possibility of recycling hydraulic fluid. In an effort to reduce the waste stream of POL products generated by military units, The DGSC Hazardous Materials Minimization Office provided funding from the Defense Environmental Restoration Account (DERA) to not only demonstrate that hydraulic fluid could be recycled, but to also evaluate commercial recycling technology. Most often, even though hydraulic fluid can contain significant water and particulate contamination, the additive package which provides the fluid's desired performance remains in tact. If hydraulic fluid can be recycled by removing contamination, and the clean fluid determined to retain sufficient performance capabilities, a reduction in the POL waste stream would result because the recycled fluid could be returned to service.[1] Recycling the fluid will not only reduce disposal costs, but also significantly reduce new fluid procurement costs.

In demonstrating the recyclability of hydraulic fluid, this investigation was limited to MIL-H-46170 hydraulic fluid (FRH).[2] The objective of the investigation was to characterize any loss of performance of the used fluid, identify effective means of recycling the fluid, and demonstrating satisfactory performance of the recycled fluid. Two issues were addressed in this effort. First, the fluid was evaluated in the laboratory to determine the viability of recycling hydraulic fluid. The data gained from this investigation provides the baseline for evaluating commercially available recycling technology. Not only must it be proven on a laboratory scale that the fluid can be recycled but also that large quantities generated by maintenance units and depots can be recycled using commercial technology. The effort in the laboratory sets the stage for evaluating the viability of recycling on a large scale.

Section 2 Technical Approach

In demonstrating that hydraulic fluid can be recycled and returned to service, three tasks were performed. First, used fluid was evaluated against specification requirements to identify any loss of fluid performance. Second, techniques were developed for removing the water and particulate contamination present in the used fluid. Finally, techniques were developed for returning the recycled fluid to specification performance. Table 1 provides a summary of the performance requirements as specified in MIL-H-46170. These requirements must be met by the recycled fluid before it can be successfully returned to service.

Table 1. MIL-H-46170 Fluid Performance Requirements

PERFORMANCE TEST	MIL-L-46170
Oxidation/Corrosion ASTM D4636, #3	168 hrs @ 135°C vis. chng < 10% acid # chng < + 0.30
Corrosion Inhibition ASTM D1748	100 hrs min
Galvanic Corrosion FTM 5322	10 days
Low Temp Stability FTM 3458	72 hrs @ -54°C
Pour Point ASTM D97	-60°C min
Viscosity @ 40°C ASTM D445	19.5 cSt max
Viscosity @ 100°C ASTM D445	3.4 cSt min
Viscosity @ -40°C ASTM D445	2600 cSt max
Viscosity @ -54°C ASTM D445	report
Solid particle Count MIL-H-46170	10,000 max @ 5-25 micrometers
Solid Particle Count -H-46170	250 max @ 26-50 micrometers
Solid Particle Count MIL-H-46170	50 max @ 51-100 micrometers

Table 1. MIL-H-46170 Fluid Performance Requirements (continued)

PERFORMANCE TEST	MIL-L-46170
Solid Particle Count MIL-H-46170	10 max @ over 100 micrometers
Acid Number ASTM D664	0.2 gm KOH/gm max
Elastomer Swell FTM 3603	-
Nitrile	0% - 3%
Fluorocarbon	0% - 1%
Fluorosilicone	0% - 2%
Polyacrylate	0% - 2%
Polyurethane	0% - 1%
Evaporation Loss ASTM D972	5% max
Steel on Steel Wear ASTM D4172	0.3 mm max @ 10 kg load
Steel on Steel Wear ASTM D4172	0.65 mm max @ 40 kg load
Foam Characteristics ASTM D892	65 ml max
Water Content ASTM D1744	500 ppm max
Flash Point ASTM D92	204°C min
Fire Point ASTM D92	246° min
Storage Stability FTM 3465	12 months

The task of recycling the hydraulic fluid is one of removing unwanted contaminants and treating the fluid to bring performance back to specification requirements. The effects of contamination in a hydraulic system can be disastrous. Solid particle contamination in the fluid can cause wear and jamming. Additionally, a domino effect can take place because wear of the surfaces exposes clean metal which is then subjected to corrosive attack if moisture is present in the system. It is vital in recycling hydraulic fluid that particulate and moisture contamination be removed otherwise the additives in the fluid will be hampered in their ability to provide protection.[3]

Removing the particulate contamination in the laboratory was relatively straight forward but time consuming. The fluid was first centrifuged to remove any large sediment contamination. The centrifuged fluid was then subjected to a series of successively smaller filters (5.0 microns, 0.8 microns, 0.45 microns) until the particle count fell below the maximum allowed by the specification.

One technique for removing water contamination involves dilution of the hydraulic fluid with a water-immiscible solvent that will separate the water into an immiscible layer then co-distilling the off the water and solvent. This technique is recommended if large amounts of water are present. Used fluid that was obtained from Aberdeen Proving Ground was found to contain only 728 ppm water thus a different technique was employed, which although simpler, could prove to be time consuming.

The used fluid was simply heated to 109°C for a period of time. The amount of time required depended on the volume of fluid being de-humidified and degree of water contamination. One liter of fluid containing less than 0.1% water required only 2 hours of exposure at 109°C. Fluid containing greater than 0.5% water required 24 hours to de-humidify 1 liter. Heating the fluid to 109°C was sufficient enough to drive of any water yet not stress the fluid thermally. In most cases the water content was reduced to half of the maximum (500 ppm) allowed. While the techniques used in the laboratory proved effective, they are not the techniques of choice for recycling hydraulic fluid on the premises of maintenance units and depots. The technology required must allow for high volumes in a short amount of time. In most cases, this can only be accomplished through filtering technology that removes all types of contamination.

Section 3 Results

Table 2 below summarizes the results of all testing performed on the used and recycled fluids. Comparison of the results summarized in this table with the requirements identified in Table 1 indicate that the used fluid does not provide adequate performance in Low Temperature Stability, Water Content, Foaming Characteristics, Fire Point, Particle Count, and Evaporation Loss. The recycled fluid, however, demonstrated an immediate improvement in Low Temperature Stability, Water Content, Particle Count, and Evaporation Loss on simply removing the particulate and water contamination. The recycled fluid still did not exhibit satisfactory performance in Foaming Characteristics or Fire Point.

Table 2. Fluid Performance — Used and Recycled

TEST	USED FRH	RECYCLED FRH
5308 ACID NO.	0.22	0.36
5308 COUPON WT CHNG	PASS	PASS
5308 Δ VISCOSITY	9.6%	3.9%
HUMIDITY CABINET	PASS	PASS
GALVANIC CORROSION	PASS	PASS
LOW TEMP STABILITY	FAIL	PASS
VISCOSITY -40 °C	2506 cSt	2494 cSt
VISCOSITY 40 °C	15.7 cSt	16.4 cSt
VISCOSITY 100 °C	3.8 cSt	4.2 cSt
POUR PT	Below -60°C	Below -60°C
FLASH PT	211°C	208°C
FIRE PT	233°C	224°C
WATER CONTENT (PPM)	728	278
FOAMING	80/0, 30/0, 60/0	90/0, 30/0, 60/0
4-BALL WEAR	0.382 mm	0.355 mm
ACID NUMBER	0.25 mg KOH/mg	0.15 mg KOH/mg
PARTICLE COUNT (MICROMETERS)	127,347 (5-25) 32 (26-50) 2 (51-100) 0 (OVER 100)	1,257 (5-25) 19 (26-50) 1 (51-100) 0 (OVER 100)
EVAPORATION LOSS	5.95%	4.36%
ELASTOMER SWELL	—	—
NITRILE	1.78%	1.45%
FLUOROCARBON	0.46%	0.39%
FLUOROSILICONE	2.04%	2.4%
POLYACRYLATE	1.06%	1.44%
POLYURETHANE	0.37%	-0.26%

Given that the recycled fluid failed only the foaming characteristics, only minor treatment of the fluid would be required to bring the fluid within specifications. Instead of adding additional anti-foaming agent to solve the problem, new FRH from an unopened can was added to the recycled fluid. Two mixtures were created to identify the maximum and minimum fluid ratios. New FRH was mixed with recycled FRH in 25:75 and 50:50 ratios. These fluid mixtures were evaluated against the same performance criteria with results summarized in Table 3 below.

Table 3. Performance of Recycled FRH Mixed with New FRH

TEST	25:75 FRH MIX	50:50 FRH MIX
5308 ACID NO.	0.13 mg KOH/mg	0.21 mg KOH/mg
308 COUPON WT CHNG	PASS	PASS
5308 Δ VISCOSITY	-1.34%	-4.42%
HUMIDITY CABINET	PASS	PASS
GALVANIC CORROSION	PASS	PASS
LOW TEMP STABILITY	PASS	PASS
VISCOSITY -40 °C	2473 cSt	2183 cSt
VISCOSITY 40 °C	16.4 cSt	17.0 cSt
VISCOSITY 100 °C	3.9 cSt	3.8 cSt
POUR PT	Below -60°C	Below -60°C
FLASH PT	212°C	210°C
FIRE PT	230°C	236°C
WATER CONTENT (PPM)	324.5	342.1
FOAMING	55/0,30/0 50/0	55/0,30/0 50/0
4-BALL WEAR	0.34 mm	0.37 mm
ACID NUMBER	0.21 gm KOH/gm	0.15 gm KOH/gm
PARTICLE COUNT (MICROMETERS)	Not Necessary	Not Necessary
EVAPORATION LOSS	3.84%	3.30%
ELASTOMER SWELL	—	—
NITRILE	1.67%	2.24%
FLUOROCARBON	0.19%	0.81%
FLUOROSILICONE	1.62%	1.91%
POLYACRYLATE	0.71%	2.53%
POLYURETHANE	-0.50%	-0.11%

As can be seen, both fluid mixtures passed all performance requirements except the Fire Point. The foaming characteristics tested below the maximum allowed in the specification. Evaporation Loss, Flash Point, Fire Point, and corrosion/oxidation stability (5308 test) all improved with the addition of the new fluid. Neither fluid mixture, however, passed the Fire Point requirement. The 25% mixture exhibited a Fire

Point of 16°C below the minimum while the 50% mixture exhibited a Fire Point 10°C below the minimum. Although some improvement in Fire Point occurred, there seems to be no significant performance improvement of the 50% mixture over the 25% mixture.

Section 4 Conclusions

While recycled FRH does not meet all specification performance requirements, it can be treated with new FRH to improve fluid performance to specification standards. Although adding new fluid to the recycled fluid did not bring the fire point completely up to the specification requirement, the fluid mixture did meet the flash point and all other requirements. A loss in Fire Point of 10-16°C does not imply a significant loss in fire resistance. Keeping the flash point up to specification standard indicates the fire resistance of the fluid remains predominantly in tact. In evaluating the merits of recycling hydraulic fluid, the negative aspects are simply the slight loss in fire point whereas the positive aspects are the reduction in waste stream and associated costs.

Costs of recycling will be limited to the recycling process itself, with no expenses going toward procurement of additives to extend the service life of the fluid. Treating the recycled fluid with new FRH precludes the difficulties that are inherent in trying to add new additives to a formulated fluid. There will be no danger of adding too much additive and causing instability or too little additive and not meeting performance requirements. Since hydraulic fluid cannot be recycled indefinitely, some procurement of new fluid will always take place, thus a ready source of new fluid to mix with the recycled fluid will always be available. Even though the recycled fluid must be mixed with new FRH, significant savings will result because the waste stream will be reduced thus lowering disposal costs and procurement volumes of new fluid will lessen.

The efforts discussed in this report were limited to proving on a laboratory scale that FRH could be recycled and returned to service. This is just the first step prior to implementing a hydraulic fluid recycling program throughout the military. The next phase of this investigation is to evaluate commercial recycling technology to verify that the fluid can be recycled to meet specification performance on a large scale. Once successful commercial units have been identified, a field test of the units themselves and the recycled fluid in actual vehicles will be conducted. In addition, efforts will also be aimed at performing oil analysis on the used and recycled fluids to better identify the types of solid particulate contamination found in the used fluid and removed in the recycling process.

References

1. MIL-HDBK-118, *Military Handbook: Design Guide for Military Applications of Hydraulic Fluids,* 1993, p. 1-9.

2. MIL-H-46170, *Hydraulic Fluid, Rust Inhibited, Fire Resistant, Synthetic Hydrocarbon.*

3. MIL-HDBK-118, *Military Handbook: Design Guide for Military Applications of Hydraulic Fluids,* 1993, p. 7-6 - 7-8.

4. MIL-HDBK-118, *Military Handbook: Design Guide for Military Applications of Hydraulic Fluids,* 1993, p. 7-11.

5. Van Brocklin, Constance, *Determination of MIL-H-6083 Hydraulic Fluid In-Service Use Limits for Self Propelled Artillery,* USA-BRDEC-TR//2512, 1991, p. 5.

Distribution for TARDEC Technical Report 13619

DEPARTMENT OF THE ARMY

HQDA
1 ATTN DALO TSE
1 ATTN DALO SM
PENTAGON
WASHINGTON DC 20310-0103

CDR AMC
1 ATTN AMCRD S
1 ATTN AMCRD E
1 ATTN AMCRD IM
1 ATTN AMCRD IT
1 ATTN AMCRDA
1 ATTN AMCRD MS
1 ATTN AMCRD MT
1 ATTN AMCICP ISI
5001 EISENHOWER AVE
ALEXANDRIA VA 22333-0001

TARDEC
1 ATTN AMSTA CMA
1 ATTN AMSTA CMB
1 ATTN AMSTA CME
1 ATTN AMSTA N
1 ATTN AMSTA R
1 ATTN AMSTA RG
1 ATTN AMCPM ATP
1 ATTN AMSTA Q
1 ATTN AMSTA UE
1 ATTN AMSTA UG
CDR TACOM
WARREN MI 48397-5000

CDR ARMY TACOM
1 ATTN AMSTA FP
1 ATTN AMSTA KL
1 ATTN AMSTA MM
1 ATTN AMSTA MT
1 ATTN AMSTA MC
1 ATTN AMSTA GT
1 ATTN AMSTA FNG
1 ATTN AMSTA FR
1 ATTN USMC LNO
1 ATTN AMSPM LAV
1 ATTN AMSPM 113/M60
1 ATTN AMCPM CCE/SMHE
WARREN MI 48397-5000

TARDEC
20 ATTN AMSTA-RBF
CDR TACOM
10101 GRIDLEY RD STE 128
FT BELVOIR, VA 22060-5843

PROG EXEC OFFICER
ARMORED SYS MODERNIZATION
1 ATTN SFAE ASM S
1 ATTN SFAE ASM BV
1 ATTN SFAE ASM CV
1 ATTN SFAE ASM AG
CDR TACOM
WARREN MI 48397-5000

PROG EXEC OFFICER
ARMORED SYS MODERNIZATION
1 ATTN SFAE ASM FR
1 ATTN SFAE ASM AF
PICATINNY ARSENAL
NJ 07806-5000

PROG EXEC OFFICER
COMBAT SUPPORT
1 ATTN SFAE CS TVL
1 ATTN SFAE CS TVM
1 ATTN SFAE CS TVH
CDR TACOM
WARREN MI 48397-5000

PROG EXEC OFFICER
ARMAMENTS
1 ATTN SFAE AR HIP
1 ATTN SFAE AR TMA
1 PICATINNY ARSENAL
NJ 07806-5000

PROJ MGR
UNMANNED GROUND VEH
1 ATTN AMCPM UG
REDSTONE ARSENAL
AL 35898-8060

DIR
ARMY RSCH LAB
1 ATTN AMSRL CP PW
2800 POWDER MILL RD
ADELPHIA MD 20783-1145

VEHICLE PROPULSION DIR
1 ATTN AMSRL VP (MS 77 12)
NASA LEWIS RSCH CTR
21000 BROOKPARK RD
CLEVELAND OH 44135

CDR AMSAA
1 ATTN AMXSY CM
1 ATTN AMXSY L
APG MD 21005-5071

CDR ARO
1 ATTN AMXRO EN (D MANN)
RSCH TRIANGLE PK
NC 27709-2211

DIR
AMC PKG STO CONT CTR
1 ATTN SDSTO TE S
TOBYHANNA PA 18466-5097

CDR AEC
1 ATTN SFIM AEC ECC (T ECCLES)
APG MD 21010-5401

CDR ARMY ATCOM
1 ATTN AMSAT I ME (L HEPLER)
1 ATTN AMSAT I LA (V SALISBURY)
1 ATTN AMSAT R EP (V EDWARD)
4300 GOODFELLOW BLVD
ST LOUIS MO 63120-1798

CDR AVIA APPL TECH DIR
1 ATTN AMSAT R TP (H MORROW)
FT EUSTIS VA 23604-5577

CDR ARMY NRDEC
1 ATTN SATNC US (SIEGEL)
1 ATTN SATNC UE
NATICK MA 01760-5018

CDR ARMY ARDEC
1 ATTN SMCAR CC
1 ATTN SMCAR ESC S
PICATINNY ARSENAL
NJ 07808-5000

CDR ARMY CRDEC
1 ATTN SMCCR RS
APG MD 21010-5423

CDR ARMY DESCOM
1 ATTN AMSDS MN
1 ATTN AMSDS EN
CHAMBERSBURG PA 17201-4170

CDR ARMY AMCCOM
1 ATTN AMSMC MA
ROCK ISLAND IL 61299-6000

CDR ARMY WATERVLIET ARSN
1 ATTN SARWY RDD
WATERVLIET NY 12189

DIR AMC LOG SPT ACT
1 ATTN AMXLS LA
REDSTONE ARSENAL
AL 35890-7466

CDR APC
1 ATTN SATPC Q
1 ATTN SATPC QE (BLDG 85 3)
NEW CUMBERLAND
PA 17070-5005

1 PETROL TEST FAC WEST
BLDG 247 TRACEY LOC
DDRW
P O BOX 96001
STOCKTON CA 95296-960

CDR ARMY LEA
1 ATTN LOEA PL
NEW CUMBERLAND
PA 17070-5007

CDR ARMY TECOM
1 ATTN AMSTE TA R
1 ATTN AMSTE TC D
1 ATTN AMSTE EQ
APG MD 21005-5006

PROJ MGR PETROL WATER LOG
1 ATTN AMCPM PWL
4300 GOODFELLOW BLVD
ST LOUIS MO 63120-1798

PROJ MGM MOBILE ELEC PWR
1 ATTN AMCPM MEP
7798 CISSNA RD STE 200
SPRINGFIELD VA 22150-3199

CDR
ARMY COLD REGION TEST CTR
1 ATTN STECR TM
1 ATTN STECR LG
APO AP 96508-7850

CDR
ARMY BIOMED RSCH DEV LAB
1 ATTN SGRD UBZ A
FT DETRICK MD 21702-5010

CDR FORSCOM
1 ATTN AFLG TRS
FT MCPHERSON GA 30330-6000

CDR TRADOC
1 ATTN ATCD SL 5
INGALLS RD BLDG 163
FT MONROE VA 23651-5194

CDR ARMY ARMOR CTR
1 ATTN ATSB CD ML
1 ATTN ATSB TSM T
FT KNOX KY 40121-5000

CDR ARMY QM SCHOOL
1 ATTN ATSM CD
1 ATTN ATSM PWD
FT LEE VA 23001-5000

CDR
ARMY COMBINED ARMS SPT CMD
1 ATTN ATCL CD
1 ATTN ATCL MS
FT LEE VA 23801-6000

CDR ARMY FIELD ARTY SCH
1 ATTN ATSF CD
FT SILL OK 73503

CDR ARMY TRANS SCHOOL
1 ATTN ATSP CD MS
FT EUSTIS VA 23604-5000

CDR ARMY INF SCHOOL
1 ATTN ATSH CD
1 ATTN ATSH AT
FT BENNING GA 31905-5000

CDR ARMY AVIA CTR
1 ATTN ATZQ DOL M
1 ATTN ATZQ DI
FT RUCKER AL 36362-5115

CDR ARMY CACDA
1 ATTN ATZL CD
FT LEAVENWORTH KA 66027-5300

CDR ARMY ENGR SCHOOL
1 ATTN ATSE CD
FT LEONARD WOOD
MO 65473-5000

CDR ARMY ORDN CTR
1 ATTN ATSL CD CS
APG MD 21005

CDR ARMY SAFETY CTR
1 ATTN CSSC PMG
1 ATTN CSSD SPS
FT RUCKER AL 36362-5363

CDR ARMY CSTA
1 ATTN STECS EN
1 ATTN STECS LI
1 ATTN STECS AE
1 ATTN STECS AA
APG MD 21005-5059

CDR ARMY YPG
1 ATTN STEYP MT TL M
YUMA AZ 85365-9130

CDR ARMY CERL
1 ATTN CECER EN
P O BOX 9005
CHAMPAIGN IL 61826-9005

1 DIR
AMC FAST PROGRAM
10101 GRIDLEY RD STE 104
FT BELVOIR VA 22060-5818

CDR I CORPS AND FT LEWIS
1 ATTN AFZH CSS
FT LEWIS WA 98433-5000

CDR
RED RIVER ARMY DEPOT
1 ATTN SDSRR M
1 ATTN SDSRR Q
TEXARKANA TX 75501-5000

PS MAGAZINE DIV
1 ATTN AMXLS PS
DIR LOGSA
REDSTONE ARSENAL
AL 35898-7466

CDR 6TH ID (L)
1 ATTN APUR LG M
1060 GAFFNEY RD
FT WAINWRIGHT
AK 99703

DEPARTMENT OF THE NAVY

OFC OF NAVAL RSCH
1 ATTN ONR 464
800 N QUINCY ST
ARLINGTON VA 22217-5660

CDR
NAVAL SEA SYSTEMS CMD
1 ATTN SEA 03M3
2531 JEFFERSON DAVIS HWY
ARLINGTON VA 22242-5160

CDR
NAVAL SURFACE WARFARE CTR
1 ATTN CODE 632
1 ATTN CODE 859
3A LEGGETT CIRCLE
ANNAPOLIS MD 21401-5067

CDR
NAVAL RSCH LABORATORY
1 ATTN CODE 6181
WASHINGTON DC 20375-5342

CDR
NAVAL AIR WARFARE CTR
1 ATTN CODE PE33 AJD
P O BOX 7176
TRENTON NJ 08628-0176

1 CDR
NAVAL PETROLEUM OFFICE
CAMERON STA T 40
5010 DUKE STREET
ALEXANDRIA VA 22304-6180

1 OFC ASST SEC NAVY (I 7 E)
CRYSTAL PLAZA 5
2211 JEFFERSON DAVIS HWY
ARLINGTON VA 22244-5110

CDR
NAVAL AIR SYSTEMS CMD
1 ATTN AIR 53623C
1421 JEFFERSON DAVIS HWY
ARLINGTON VA 22243-5360

DEPARTMENT OF THE NAVY
U.S. MARINE CORPS

HQ USMC
1 ATTN LPP
WASHINGTON DC 20380-0001

1 PROG MGR COMBAT SER SPT
MARINE CORPS SYS CMD
2033 BARNETT AVE STE 315
QUANTICO VA 22134-5080

1 PROG MGR GROUND WEAPONS
MARINE CORPS SYS CMD
2033 BARNETT AVE

QUANTICO VA 22134-5080
1 PROG MGR ENGR SYS
MARINE CORPS SYS CMD
2033 BARNETT AVE
QUANTICO VA 22134-5080

CDR
MARINE CORPS SYS CMD
1 ATTN SSE
2033 BARNETT AVE STE 315
QUANTICO VA 22134-5010

CDR
BLOUNT ISLAND CMD
1 ATTN CODE 922/1
814 RADFORD BLVD
JACKSONVILLE
FLA 32226-3404

CDR
MARINE CORPS LOGISTICS BA
1 ATTN CODE 837
814 RADFORD BLVD
ALBANY GA 31704-1128

1 CDR
2ND MARINE DIV
PSC BOX 20090
CAMP LEJEUNNE
NC 28542-0090

1 CDR
1ST MARINE DIV
CAMP PENDLETON
CA 92055-5702

1 CDR
FMFPAC G4
BOX 64118
CAMP H M SMITH
HI 96861-4118

DEPARTMENT OF DEFENSE

ODUSD
1 ATTN (L) MRM
PETROLEUM STAFF ANALYST
PENTAGON
WASHINGTON DC 20301-8000

ODUSD
1 ATTN (ES) CI
400 ARMY NAVY DR
STE 206
ARLINGTON VA 22202

HQ USEUCOM
1 ATTN ECJU L1J
UNIT 30400 BOX 1000
APO AE 09128-4209

US CINCPAC
1 ATTN J422 BOX 64020
CAMP H M SMITH
HI 96861-4020

1 JOAP TSC
BLDG 780
NAVAL AIR STA
PENSACOLA FL 32408-5300

DIR DLA
1 ATTN DLA MMDI
ATTN DLA MMSB
CAMERON STA
ALEXANDRIA VA 22304-6100

CDR
DEFENSE FUEL SUPPLY CTR
1 ATTN DFSC Q BLDG 8
1 ATTN DFSC S BLDG 8
CAMERON STA
ALEXANDRIA VA 22304-6160

CDR
DEFENSE GEN SUPPLY CTR
1 ATTN DGSC SSA
1 ATTN DGSC STA
8000 JEFFERSON DAVIS HWY
RICHMOND VA 23297-5678

DIR ADV RSCH PROJ AGENCY
1 ATTN ARPA/ASTO
3701 N FAIRFAX DR
ARLINGTON VA 22203-1714

12 DEFENSE TECH INFO CTR
CAMERON STATION
ALEXANDRIA VA 22314

DEPARTMENT OF AIR FORCE

HQ USAF/LGSSF
1 ATTN FUELS POLICY
1030 AIR FORCE PENTAGON
WASHINGTON DC 20330-1030

HQ USAF/LGTV
1 ATTN VEH EQUIP/FACILITY
1030 AIR FORCE PENTAGON
WASHINGTON DC 20330-1030

AIR FORCE WRIGHT LAB
1 ATTN WL/POS
1 ATTN WL/POSF
1 ATTN WL/POSL
1790 LOOP RD N
WRIGHT PATTERSON AFB
OH 45433-7103

AIR FORCE WRIGHT LAB
1 ATTN WL/MLBT
2941 P ST STE 1
WRIGHT PATTERSON AFB
OH 45433-7750

AIR FORCE WRIGHT LAB
1 ATTN WL/MLSE
2179 12TH ST STE 1
WRIGHT PATTERSON AFB
OH 45433-7718

1 AIR FORCE MEEP MGMT OFC
615 SMSQ/LGTV MEEP
201 BISCAYNE DR STE 2
ENGLIN AFB FL 32542-5303

1 SA ALC/SFT
1014 ANDREWS RD STE 1
KELLY AFB TX 78241-5603

1 WR ALC/LVRS
225 OCMULGEE CT
ROBINS AFB
GA 31098-1647